



# Innershield® NR®-FAB-70

Low Alloy, Flat & Horizontal • AWS E70T7-G

## Key Features

---

- ▶ Proprietary design increases wire stiffness to aid feedability and promotes a smooth arc transfer.
- ▶ Capable of producing weld deposits with impact properties exceeding an average of 54 J (40 ft•lbf) at -29°C (-20°F).
- ▶ Meets FEMA 353 and AWS D1.8 seismic lot waiver requirements

## Conformances

---

AWS A5.29/A5.29M: 2005 E70T7-G  
ASME SFA-5.29 E70T7-G  
FEMA 353  
AWS D1.8

## Welding Positions

---

Flat & Horizontal

## Typical Applications

---

- ▶ Structural fabrication

## Notes

---

- ▶ Welding at high heat input procedures and slow travel speeds will significantly reduce the risk of slag entrapment.

**Innershield® NR® -FAB-70**

(AWS E70T7-G)

**DIAMETERS / PACKAGING**

Diameter in (mm)	25 lb (11.3 kg) Plastic Spool	25 lb (11.3 kg) Plastic Spool (Vacuum Sealed Foil Bag)
3/32 (2.4)	ED033628	ED033631

**MECHANICAL PROPERTIES<sup>(1)</sup> – As Required per AWS A5.29/A5.29M: 2005**

	Yield Strength <sup>(2)</sup> MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Hardness Rockwell B	Charpy V-Notch J (ft•lbf) @ -29°C (-20°F)
Requirements - AWS E70T7-G	400 (58) min.	485-620 (70-90)	20	Not Specified	Not Specified
Typical Results <sup>(3)</sup> - As Welded	405-480 (59-70)	510-570 (74-83)	23-28	88	96-162 (71-120)

**CHEMICAL COMPOSITION<sup>(1)</sup> – As Required per AWS A5.29/A5.29M: 2005**

	%C	%Mn	%Si	%S	%P	%Al
Requirements - AWS E70T7-G	Not Specified	0.50 min	1.00 max	0.030 max	0.030 max	1.8 max
Typical Results <sup>(3)</sup>	0.01-0.05	2.20-2.60	0.10-0.15	0.010 max	0.010 max	0.9-1.1

**TYPICAL OPERATING PROCEDURES**

Diameter, Polarity	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
3/32 in. (2.4 mm), DC-	38 (1.5)	2.5 (100)	22-24	265	4.0 (8.7)	2.8 (6.1)	70
		3.2 (125)	23-25	320	4.9 (10.7)	3.6 (7.9)	74
		3.8 (150)	25-27	355	5.9 (13.1)	4.6 (10.1)	77
		4.6 (180)	25-27	380	7.1 (15.7)	5.5 (12.2)	77
		5.1 (200)	27-29	410	7.9 (17.5)	6.1 (13.4)	77
		5.3 (210)	27-29	425	8.2 (18.1)	6.5 (14.3)	79

<sup>(1)</sup>Typical all weld metal. <sup>(2)</sup>Measured with 0.2% offset. <sup>(3)</sup>See test results disclaimer below.NOTE: FEMA and AWS D1.8 structural steel seismic supplement test data can be found on this product at [www.lincolnelectric.com](http://www.lincolnelectric.com).

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)

### TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

### CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.