

SUPERARC® LA-100™

Low Alloy, Copper Coated ■ AWS ER100S-G, ER110S-G & EM2

KEY FEATURES

- Capable of producing welds with 690 MPa (100 ksi) tensile strength
- Excellent for welding quenched and tempered steels and HY-80 base materials
- MicroGuard® Ultra provides superior feeding and arc stability
- Supports short-circuiting, globular, axial spray and pulsed spray transfer

WELDING POSITIONS

All

SHIELDING GAS

90-95% Argon / Balance CO₂
 95-98% Argon / Balance O₂
 Flow Rate: 30 - 50 CFH

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Steel Spool	44 lb (20 kg) Steel Spool	60 lb (27.2 kg) Coil	500 lb (227 kg) Accu-Trak® Drum	500 lb (227 kg) Accu-Pak® Box
0.035 (0.9)	ED031417	EDS30778	ED010996	ED031445	ED036608
0.045 (1.1)		EDS30779		EDS01162	
1/16 (1.6)					

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.28/A5.28M

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft-lbf)	
				@ -18°C (0°F)	@ -51°C (-60°F)
Requirements – AWS ER100S-G As-Welded - Gas Not Specified	Not Specified	690 (100) min	Not Specified	Not Specified	Not Specified
AWS ER110S-G As-Welded - Gas Not Specified	Not Specified	760 (110) min	Not Specified	Not Specified	Not Specified
MIL-100S-1 per MIL-E-23765/2C, 2D, 2E & T9074-BC-G1B-010/0200 As-Welded with 98% Ar /2% O ₂	565-825 (82-120)	Not Specified	16 min.	81 (60) min	47 (35) min
Typical Results⁽³⁾ As-Welded at 30 kJ/in with 95% Ar/5% CO ₂ As-Welded at 45 kJ/in with 98% Ar/2% O ₂	750 (109) 730 (106)	790 (115) 780 (114)	22 20	164 (121) - -	138 (102) 118 (87)
Pulse As-Welded at 110 kJ/in with 95% Ar/5% CO ₂	580 (84)	745 (108)	25	138 (102)	70 (52)
CV As-Welded at 110 kJ/in with 95% Ar/5% CO ₂	620 (90)	740 (107)	25	170 (125)	106 (78)
As-Welded at 45 kJ/in with 95% Ar/5% CO ₂	682 (99)	765 (111)	20	- -	117 (86)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer

CONFORMANCES

AWS A5.28/A5.28M:	ER100S-G, ER110S-G
ASME SFA-A5.28:	ER100S-G, ER110S-G
AWS A5.23/A5.23M:	EM2
ABS:	4YQ550SA
CWB/CSA W48-06:	ER69S-G (ER100S-G)
DB:	EN 12534 T 69 5 Mn3Ni1, 5 Mo
TUV:	EN 12534 T 69 5 Mn3Ni1, 5 Mo
EN ISO 16834-B:	G 69A 5 A N3M2
MIL-E-23765/2:	MIL-100S-1

TYPICAL APPLICATIONS

- HY-80 base material
- ASTM A514, A543, A724 and A782 quenched and tempered plate
- Various heat input conditions
- Military low alloy applications

WIRE COMPOSITION – As Required per AWS A5.28/A5.28M

	%C	%Mn	%Si	%Ni	%Mo
Requirements – AWS ER100S-G, ER110S-G	-	-	-	(A)	(A)
Typical Results ⁽³⁾	0.05-0.06	1.63-1.69	0.46-0.50	1.88-1.96	0.43-0.45
	%Cr	%S	%P	%V	
Requirements – AWS ER100S-G, ER110S-G	(A)	-	-	-	
Typical Results ⁽³⁾	0.04-0.06	0.002-0.005	0.005-0.009	≤ 0.01	
	%Al	%Ti	%Zr	%Cu	
Requirements – AWS ER100S-G, ER110S-G	-	-	-	-	
Typical Results ⁽³⁾	≤ 0.01	0.03-0.04	≤ 0.01	0.11-0.14	

(A) Must have the minimum of one or more of the following: 0.50% Ni, 0.30% Cr, or 0.20% Mo.

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁵⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)
0.035 in (0.9 mm), DC+					
Short Circuit Transfer 90% Ar/10% CO ₂	9-12 (3/8-1/2)	2.5 (100)	18	80	0.7 (1.6)
		3.8 (150)	19	120	1.1 (2.4)
		6.4 (250)	22	175	1.8 (4.0)
Spray Transfer 90% Ar/10% CO ₂	9-12 (3/8-1/2)	9.5 (375)	23	195	2.7 (6.0)
		12.7 (500)	29	230	3.6 (8.0)
		15.2 (600)	30	275	4.4 (9.6)
0.045 in (1.1 mm), DC+					
Pulsed Spray Transfer ⁽⁵⁾	12-19 (1/2-3/4)	5.1 (200)	19-21	130	2.4 (5.4)
		6.4 (250)	20-23	140	3.0 (6.7)
Spray Transfer 98% Ar/2% O ₂ 95% Ar/5% CO ₂	12-19 (1/2-3/4)	8.9 (350)	27	285	4.2 (9.2)
		12.1 (475)	30	335	5.7 (12.5)
		12.7 (500)	30	340	6.0 (13.2)
0.052 in (1.3 mm), DC+					
Spray Transfer 98% Ar/2% O ₂ 95% Ar/5% CO ₂	12-25 (1/2-1) 12-25 (1/2-1)	5.3 (210)	25	325	4.8 (10.7)
		6.0 (235)	27	350	5.4 (12.0)
		7.4 (290)	28	430	6.7 (14.8)

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer ⁽⁴⁾CTWD (Contact Tip to Work Distance). Subtract 1/4 in (6.4 mm) to calculate Electrical Stickout.

⁽⁵⁾Procedures in this area are for pulse MIG mode for welding in the vertical up and overhead welding positions. Actual results are dependent on joint, material thickness, as well as wave shape and pulse frequency.

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.