

# ULTRACORE® 360™ C71

Mild Steel, All Position ▪ AWS E71T-9C-JH4

## KEY FEATURES

- Seamless design protects the flux core from environmental exposure helping to maintain low diffusible hydrogen and extend shelf life
- Copper coating offers superior feedability and extended contact tip life
- Low spatter and fume levels for less post-weld clean up and a better work environment
- Low H4 diffusible hydrogen levels minimize the risk of hydrogen induced cracking
- Premium arc performance and bead appearance

## WELDING POSITIONS

All

## CONFORMANCES

**AWS A5.20/A5.20M:** E71T-9C-JH4  
**AWS A5.29/A5.29M:** E81T1-GC-H4  
**AWS A5.36/A5.36M:** E71T1-C1A6-CS1-H4

## TYPICAL APPLICATIONS

- Offshore
- Shipbuilding
- Structural
- General Fabrication

## SHIELDING GAS

100% CO<sub>2</sub>  
 Flow rate: 42-53 CFH

## DIAMETERS / PACKAGING

Diameter in (mm)	27 lb (12.2kg) Plastic Spool
0.045 (1.1)	ED036167
0.052 (1.3)	ED036168
1/16 (1.6)	ED036169

## MECHANICAL PROPERTIES<sup>(1)</sup> – As Required per AWS A5.20/A5.20M & A5.29/A5.29M & A5.36/A5.36M

	Yield Strength <sup>(2)</sup> MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Charpy V-Notch J (ft•lbf)	
				@ -40°C (-40°F)	@ -51°C (-60°F)
<b>Requirements</b>					
AWS A5.20: E71T-9C-JH4	390 (58) min	490-670 (70-95)	22 min	27 (20) min	-
AWS A5.29: E81T1-GC-H4	470 (68) min	550-690 (80-100)	19 min	-	-
AWS A5.36: E71T1-C1A6-CS1-H4	400 (58) min	490-660 (70-95)	22 min	-	27 (20) min
<b>Typical Results<sup>(3)</sup></b>					
As-Welded with 100% CO <sub>2</sub>	510-600 (74-87)	590-650 (85-94)	24-29	60-155 (44-114)	62-137 (46-101)

<sup>(1)</sup>Typical all weld metal. <sup>(2)</sup>Measured with 0.2% offset. <sup>(3)</sup>See test results disclaimer

**DEPOSIT COMPOSITION<sup>(1)</sup> – As Required per AWS A5.20/A5.20M & A5.29/A5.29M & A5.36/A5.36M**

	%C	%Mn	%Si	%S	%P	%Ni
<b>Requirements</b>						
AWS A5.20: E71T-9C-JH4	0.12 max	1.75 max	0.90 max	0.03 max	0.03 max	0.50 max
AWS A5.29: E81T1-GC-H4	Not Specified	0.50 <sup>(4)</sup>	1.00 max	0.030 max	0.030 max	0.50 <sup>(4)</sup>
AWS A5.36: E71T1-C1A6-CS1-H4	0.12 max	1.75 max	0.90 max	0.030 max	0.030 max	0.50 max
<b>Typical Results<sup>(3)</sup></b>						
As-Welded with 100% CO <sub>2</sub>	0.04-0.08	1.19-1.41	0.37-0.47	0.003-0.005	0.012-0.013	0.35-0.38
	%Cr	%Mo	%V	%Cu	%B	Diffusible Hydrogen (mL/100g weld deposit)
<b>Requirements</b>						
AWS A5.20: E71T-9C-JH4	0.20 max	0.30 max	0.08 max	0.35 max	Not Specified	4.0 max
AWS A5.29: E81T1-GC-H4	0.30 <sup>(4)</sup>	0.20 <sup>(4)</sup>	0.10 <sup>(4)</sup>	Not Specified		
AWS A5.36: E71T1-C1A6-CS1-H4	0.20 max	0.30 max	0.08 max	0.35 max		4 max
<b>Typical Results<sup>(3)</sup></b>						
As-Welded with 100% CO <sub>2</sub>	0.02-0.03	0.00-0.01	0.01	0.23-0.28	0.003-0.004	1-4

**TYPICAL OPERATING PROCEDURES**

Diameter, Polarity Shielding Gas	CTWD <sup>(5)</sup> mm (in)	Wire Feed Speed m/min (in/min)	Voltage (volts)	Approx. Current (amps)	Melt-Off Rate kg/hr (lb/hr)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
0.045 in (1.1 mm), DC+ 100% CO <sub>2</sub>	25 (1)	6.4 (250)	24-29	175	2.7 (5.9)	2.4 (5.3)	88-93
		7.6 (300)	25-30	200	3.2 (7.0)	2.9 (6.4)	
		8.9 (350)	26-32	225	3.7 (8.2)	3.4 (7.5)	
		10.2 (400)	27-33	245	4.3 (9.4)	3.9 (8.6)	
		11.4 (450)	27-35	265	4.8 (10.6)	4.4 (9.7)	
		12.7 (500)	28-36	290	5.3 (11.7)	4.9 (10.9)	
0.052 in (1.3 mm), DC+ 100% CO <sub>2</sub>	25 (1)	5.1 (200)	23-27	200	2.8 (6.2)	2.6 (5.7)	91-93
		6.4 (250)	25-28	235	3.5 (7.7)	3.2 (7.1)	
		8.9 (350)	27-31	300	4.9 (10.8)	4.5 (10.0)	
		10.8 (425)	28-32	335	6.0 (13.1)	5.5 (12.1)	
		12.7 (500)	30-34	375	7.0 (15.4)	6.5 (14.2)	
1/16 in (1.6 mm), DC+ 100% CO <sub>2</sub>	25 (1)	3.8 (150)	23-27	230	3.1 (6.7)	2.8 (6.1)	92-96
		5.1 (200)	24-28	275	4.1 (9.0)	3.8 (8.4)	
		6.4 (250)	25-31	310	5.1 (11.3)	4.8 (10.6)	
		7.6 (300)	27-34	370	6.1 (13.5)	5.8 (12.8)	
		8.9 (350)	29-36	410	7.2 (15.8)	6.8 (15.0)	

<sup>(1)</sup>Typical all weld metal. <sup>(2)</sup>See test results disclaimer <sup>(3)</sup>In order to meet the requirements of the G group, the undiluted weld metal shall have not less than the minimum specified for one or more of the elements listed.

<sup>(4)</sup>To estimate ESQ, subtract 1/4 in (6.0 mm) from CTWD. NOTE: This product contains micro-alloying elements. Additional information available upon request

Material Safety Data Sheets (MSDS) and Certificates of Conformance are available on our website at [www.lincolnelectric.com](http://www.lincolnelectric.com)

**TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

**CUSTOMER ASSISTANCE POLICY**

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change – This information is accurate to the best of our knowledge at the time of printing. Please refer to [www.lincolnelectric.com](http://www.lincolnelectric.com) for any updated information.